

## 18521 KANEPOX LINING FREE C

### PRODUCT DESCRIPTION

**18521 KANEPOX LINING FREE C** is an epoxy-polyamine based, two component, solvent-free coating with excellent resistance to fresh water, sea water. It can be applied at high film thicknesses. It exhibits excellent curing characteristics at low temperatures with daily temperature fluctuations and/or high humidity without any surface defects such as blushing, cracking etc. It is free of benzyl alcohol and nonyl phenol.

### RECOMMENDED USE

It is used as a protective coating in the structures listed below;

- Potable and sea water pipelines & storage tanks.
- Inner surfaces of drinking water and domestic water storage tanks in industrial facilities and ships.
- Steel and concrete surfaces.

It can be used as a one coat from Im1 to Im4 immersion categories according to ISO 12944-5 & 12944-9.

### CERTIFICATES

- WRAS (NSF) – Certificate of compatibility with potable water tested according to BS 6920 Part 1 & 2
- AWWAC210 (PRA) – Certificate of internal coating suitability for steel water pipelines
- Certificate of compliance with Italy Hygiene Standard DM 174 Regulation
- Certificate of compliance with Spanish Hygiene Standard RD 140/2003 Criteria

### PRODUCT CHARACTERISTICS

Finish: Gloss	Density (g/ml) 1,25±0,10
Colour: White, Cream, Oxide Red, Grey, Blue	Spreading Rate (m <sup>2</sup> /l) 3,33 (300 microns DFT)
Thinner: –	Flash Point >100°C
Mixing Ratio (By Volume) 15,60 Parts A Comp. + 4,40 Parts B Comp.	VOC ( Volatile Organic Content) 0 g/l
Mixed Product; Volume Solids (%) ~100	Application Methods Airless spray, Roller/Brush
	Pot Life (20°C) 60 minutes

### DRYING SCHEDULE(\*)

(300 microns/12 mils film thickness)

	Dry to Touch	Hard Dry	Dry to Over Coat Minimum
5°C	36 hours	96 hours	48 hours
15°C	16 hours	72 hours	24 hours
25°C	10 hours	36 hours	14 hours
35°C	7 hours	24 hours	10 hours

Drying values are valid for defined dry film thickness and below 85% relative humidity.

Fully Cured: 7 days (20°C)

(\*) Drying time depends on temperature, humidity and film thickness.

### PACKAGING

One kit of **18521 KANEPOX LINING FREE C** is 20 l.

One pail of **18521 KANEPOX LINING FREE C** component A is 15,60 l,

One can of **KANEPOX HARDENER 0362** component B is 4,40 l.

### SHELF LIFE

Part A–1 year, Part B–1 year when the material is stored in a cool and dry place in unopened original containers.

### HEALTH/SAFETY PRECAUTIONS

Refer to the MSDS sheet prepared according to EU directives before use.

## 18521 KANEPOX LINING FREE C

### SURFACE PREPARATION

Surfaces must be dry, clean, free of oil, grease and other foreign material.

**New Steel Surfaces:** Surfaces should be blasted to near-white metal surface cleanliness according to SSPC-SP10 or ISO 8501-1 Sa 2½. Blast profile on steel should be 75-100 microns in depth. Applicable directly without primer on cleaned surfaces of small tanks and warehouses where paint application could be done in the same day. For surface cleaning which lasts a few days or longer, ~40 microns DFT holding primer should be applied as a onecoat primer.

**Concrete:** Remove loose, unsound concrete, laitance and create a surface profile by either acid etching, abrasive blasting or mechanical grinders and apply cleaning water. A properly selected sealer –Kanfloor Sealer– is applied. Surfaces must be dry and clean before application.

### APPLICATION PROCEDURES (Mixing Procedure)

**18521 KANEPOX LINING FREE C** suitable to be used with airless spray equipment based on volumetric mixing. A and B components are supplied in separate packages.

### MIXING RATIO

Base 18521 : Curing Agent 0362  
3,5 : 1 by volume

### APPLICATION PROCEDURES (Mixing Procedure)

Homogenize A and B components separately by mixing. Temperature of A and B component shall be minimum 25°C and maximum 45°C. Homogenized A and B components shall be pumped to metering unit to provide constant volumetric mixing.

### APPLICATION CONDITIONS

For the best results;

Temperature must be more than 5°C during the application and/or the curing process

**Surface temperature:** At least 3°C above dew point  
**Relative humidity:** 85% maximum.

Good ventilation is required during application.

### CLEAN UP

**KANAT THINNER 0644**

## 18521 KANEPOX LINING FREE C

### APPLICATION EQUIPMENT

(The table is a guide for 20°C)

Application Equipment	Airless Spray	Roller/ Brush
Thinner maximum	–	–
Pressure minimum (bar)	225	–
Nozzle(inch)	0,021-0,033	–

### PRECAUTIONS

- Contact KANAT Project Group for procedures, pre-treatments and durations for potable water tanks to take into service.
- It is recommended to use foil while measuring the difference between wet film thickness and dry film thickness.
- Recoating period is minimum 12–14 hours and maximum 7 days (20°C). Recoating interval depends on temperature, humidity and film thickness. If maximum recoating time is exceeded abrade surface, if the surface is highly contaminated apply pressurized fresh water cleaning before recoating.
- High temperatures decrease resistance properties of epoxy based products. Epoxy based products also have a tendency to yellowing, chalking and have limited gloss retention on exterior surfaces.
- Contact KANAT Project Group for field touch-up and maintenance procedures.
- Improper storage conditions, exposure to air due to packaging, or approaching the expiration date may result in color changes (especially in red shades) and the formation of unpleasant odors in light-colored paints.

**Disclaimer:** This product is for professional users only. In case of non-compliance with the instructions or conditions set forth in this document and other additional documents regarding the application of the product, Kanat Paints & Coatings does not accept any responsibility for any damage including but not limited to performance issues. Kanat Paints & Coatings owns all trademarks, patents and licenses mentioned in this document. All values and ratios stated are given in accordance with other values and ratios in the document. All information regarding the product is correct and appropriate to the best of Kanat Paints & Coatings' knowledge, but the factors that are not related to production process, especially external factors, and that may affect the application or use are beyond the control of Kanat Paints & Coatings. It is the user's responsibility to check the validity of this document before using the product. Technical data and instructions published by Kanat Paints & Coatings may change without prior notice. Please contact Kanat Paints for current versions or additional technical data and instructions.